

Scarborough



Colour Range



Sugar



Sorbet




Biscuit



Oyster




Pepper



Treacle



Cocoa*



Liquorice

Internal Translucent & Blockout Fabric

Roller Blind | Roman Shade | Panel Glide
3.0m width

Scarborough

Technical Information

	Translucent	Blockout	
Composition:	100% Polyester with Clear Acrylic Coating	100% Polyester with Acrylic Foam Coating	
Thickness:	0.75mm ± 10%	0.80mm ± 10%	
Weight:	250 gsm ± 10%	455 gsm ± 10%	
Cutting*:	Ultrasonic Cut	Knife, Crush or Pressure Cut	
Colourfastness:	6-7 Blue Scale (AS 2001.4.21)		
Features:	Proudly Made in Australia		
Fire Retardancy Information for NON FR Products[^]:	Suitable for all building classes except Class 9(b) entertainment venues. A summary of BCA requirements can be provided on request. [^] Fabrics which are not FR treated, have been FR tested and have a Flammability result over 6 or fabrics which are not FR treated and have not undergone FR testing.		
Range:	Item:	Width:	Roll Length:
	Translucent - 8SCA300XXH	3000mm	30 metres
	Blockout - 8SCA3300XXH	3000mm	25 metres
Care & Cleaning	Dusting with a feather duster is all that is required to keep your fabric looking good. For the removal of stains, dirt and grime, gently wipe fabric skins with a sponge soaked in lukewarm water. If marks are still visible, add a little detergent. Then dry gently with a clean cloth. Test in inconspicuous area before spot cleaning.		

For more information contact us on:
hdcustservice@hunterdouglas.com.au

turnilscollage.com.au

Note: Colours are as accurate as the printing process allows. * Not available in Translucent. Please refer to the fabric swatch. © Copyright 2019 Hunter Douglas Limited [A.B.N. 98 009 675 709]

® Turnils is a registered Trade Mark of Hunter Douglas Scandinavia AB. ® Registered Trade Marks of Hunter Douglas Limited. ™ Hunter Douglas Limited has applied for the registration of the Trade Mark Collage.

Note: Warranty Conditions apply; refer to www.turnilscollage.com.au for more details. * We recommend testing all cutting and welding methods prior to use, to confirm they meet your individual fabrication specifications. 06/2019