









Avila

5
FIVE YEAR
FABRIC
WARRANTY

AUSTRALIAN
MADE

Colour Range



Internal Blockout Fabric

Roller Blind | Roman Shade | Panel Glide
3.0m width

Technical Information

Blockout

| | |
|------------------------|-------------------------------|
| Composition: | 100% Polyester |
| Thickness: | 0.46mm ± 10% |
| Weight: | 415 gsm ± 10% |
| Cutting*: | Ultrasonic, Aeronaut cut |
| Colourfastness: | 6-7 Blue Scale (AS 2001.4.21) |
| Features: | Proudly Made in Australia |

Fire Retardancy Information for NON FR Products[^]: Suitable for all building classes **except** Class 9(b) entertainment venues. A summary of BCA requirements can be provided on request.
[^] Fabrics which are not FR treated, have been FR tested and have a Flammability result over 6 or fabrics which are not FR treated and have not undergone FR testing.

| | | | |
|---------------|-----------------------|---------------|---------------------|
| Range: | Item: | Width: | Roll Length: |
| | Blockout - 82.633.9XX | 3000mm | 27 metres |

Care & Cleaning Dusting with a feather duster is all that is required to keep your fabric looking good. For the removal of stains, dirt and grime, gently wipe fabric skins with a sponge soaked in lukewarm water. If marks are still visible, add a little detergent. Then dry gently with a clean cloth. Test in inconspicuous area before spot cleaning.

Thermal & Visual Properties

| Colour | Thermal Comfort | | | Glazing & Fabric | | | | Visual Comfort |
|--------|-----------------|----|----|------------------|--------|--------|--------|----------------|
| | Ts | Rs | As | GTOT A | GTOT B | GTOT C | GTOT D | TL / TV |
| White | 0 | 64 | 36 | 33.3 | 36.2 | 35.6 | 25 | 0 |
| Pewter | 0 | 69 | 31 | 30.8 | 34 | 34.2 | 24.6 | 0 |
| Black | 0 | 66 | 34 | 32.9 | 35.8 | 35.4 | 24.9 | 0 |

Solar protection indicators are laboratory-tested. The most relevant and widely used thermal comfort factors include:

THERMAL COMFORT

Fabric Only
 Ts Solar Transmittance (%)
 Rs Solar Reflectance (%)
 As Solar Absorbance (%)
Solar radiation is always partially transmitted through, absorbed or reflected by the fabric. The sum of all 3 equals 100. Ts + Rs + As = 100% of solar energy.

GLAZING & FABRIC

Test data has been supplied using the following glazing types:
 •A Clear single glazing (4mm float)
 •B Clear double glazing (4mm float + 12mm space + 4mm float)
 •C Double glazing low-e coating and argon filled (4mm float + 16mm space + 4mm float)
 •D Reflective double glazing with low-e coating and argon filled (4mm + 16mm space + 4mm float)

GTOT (RANGE 0-1)

The Solar Heat Gain Coefficient (SHGC), measures the window's (fabric and glass) ability to transmit solar energy into a room. The SHGC is commonly referred to as g-tot. SHGC/g-tot is a calculation of the g-values of the solar protection device (fabric) and the glazing (A, B, C, D). The lower the GTOT value, the greater its ability to insulate against solar heat build-up.

VISUAL COMFORT

Fabric Only
 TL / TV Light Transmittance (%)
 RL Light Reflectance (%)

The fenestration property tests were conducted in accordance with EN 410 (1998), EN 14501:(2005), and EN 14500:(2008).

For more information contact us on:
hdcustservice@hunterdouglas.com.au

turnilscollage.com.au